

Green moisture content and basic density of 95 woody species growing in Kyushu University Forests, Japan

Toshihiro UMEBAYASHI*, Shinya KOGA**, Yasuhiro UTSUMI**, Susumu INOUE**, Yasuki SHIIBA**, Hisami NAGASAWA**, Shigeru OSAKI**, Katsuyoshi KUBOTA**, Sachiko INOUE**, Junji MATSUMURA*** and Kazuyuki ODA***

We investigated the green moisture content and basic density of 95 woody species growing in Kyushu University Forests. In softwood species, the green moisture content of heartwood ranged from 28% in *Cryptomeria japonica* to 67% in *Abies firma*, and in sapwood, from 75% in *Tsuga sieboldii* to 160% in *Cryptomeria japonica*. The green moisture content of softwood trees was greater in sapwood than heartwood. The green moisture content in the heartwood of hardwood species ranged from 34% in *Euonymus alatus* f. *striatus* to 83% in *Kalopanax pictus*, and in sapwood, from 45% in *Fraxinus sieboldiana* to 153% in *Actinidia polygama*. We found three radial variation pattern types in stems of hardwood species. The green moisture content was higher in heartwood than sapwood, in the first type, whereas in the second, it was higher in sapwood than heartwood. In a third type, differences between heartwood and sapwood were relatively small. The basic density of softwood species ranged from 378 kg/m³ in *Cryptomeria japonica* to 524 kg/m³ in *Tsuga sieboldii*. Most trees tended to decrease in basic density from corewood to outerwood. Basic density in hardwood species ranged from 266 kg/m³ in *Paulownia tomentosa* to 751 kg/m³ in *Rhaphiolepis indica* var. *umbellata*. We identified three types of radial variation pattern in stems of hardwood species. In the first type, basic density was higher in corewood than outerwood, whereas in second, it was higher in outerwood. In the third type, differences between corewood and outerwood were small. We also provided the information on the age and size of heartwood formation.

Keyword : green moisture content; basic density; Kyushu University Forests; Japan

国内に生育する樹木の木材性質に関するデータベースを作成する一環として、九州大学演習林（北海道演習林，宮崎演習林，福岡演習林）に生育するつる性木本植物3樹種を含む95樹種の生材含水率および容積密度数を測定した。針葉樹の生材含水率は辺材が心材より常に大きく，心材ではスギの28%からモミの67%の範囲にあり，辺材ではツガの75%からスギの160%の範囲にあった。一方，広葉樹の生材含水率は，心材ではヌルデの34%からハリギリの83%の範囲にあり，辺材ではアオダモの45%からマタタビの153%の範囲にあった。樹幹半径方向の生材含水率のパラツキについては，辺材よりも心材が高いタイプ，心材よりも辺材が高いタイプ，心材と辺材にほとんど差がないタイプの3タイプが認められた。針葉樹材の容積密度数は，スギの378 kg/m³からツガの524 kg/m³の範囲にあり，樹幹半径方向の変動では，中心部が外周部よりも高かった。広葉樹材の容積密度数は，キリの266 kg/m³からシャリンバイの751 kg/m³の範囲にあり，樹幹半径方向の変動では，外周部よりも中心部が高いタイプ，中心部よりも外周部が高いタイプ，中心部と外側部にほとんど差がないタイプの3タイプが認められた。最後に心材形成を開始する樹齢やサイズに係わる情報について記載した。キーワード：生材含水率，容積密度数，九州大学演習林，日本

1 . Introduction

Wood moisture strongly affects wood quality characteristics, including physical and mechanical properties, dimensional stability, machining, drying performance, adhesion properties, durability, burning characteristics, and transport efficiency (e.g., Watanabe 1978 ; Fushitani *et al.* 1989; Forestry and Forest Products

Research Institute 2004). Thus, wood moisture content is of concern to foresters, wood processors, and users at every stage from standing trees to the service performance of various wood products.

Living trees contain a large amount of water in their stems, because they transport water from the soil to their leaves via their stems, and also store some water in their stems (Tyree & Zimmermann 2002). Previous studies

* Department of Forest and Forest Products Science, Graduate School of Bioresource and Bioenvironmental Sciences, Kyushu University, Hakozaki, Fukuoka, 812-8581

(Present address: Research Team for Detection of Plant Pathogens and Nematodes, National Agricultural Research Center)

九州大学大学院生物資源環境科学府森林資源科学専攻

(現所属：中央農業総合研究センター病害虫検出同定法研究チーム)

** University Forests, Faculty of Agriculture, Kyushu University, Kasuya, Fukuoka, 811-2415

九州大学農学部附属演習林

*** Sustainable Bioresource science, Agro-Environmental Sciences, Faculty of Agriculture, Kyushu University, Hakozaki, Fukuoka, 812-8581
九州大学大学院農学研究院環境農学部門サステナブル資源科学

reported wood moisture content (green moisture content) of living trees growing in Japan. For example, Yazawa *et al.* (1965) reported interspecies variation in green moisture content distribution in the stems of nine hardwood species. Nakada (2006) investigated water distribution in the stems of 11 softwood species. Kawazumi *et al.* (1991) and Nakada *et al.* (1999) reported intraspecies variation in green moisture content in the stems of *Cryptomeria japonica*. Previous studies also have reported seasonal variations in *Fagus crenata* (Yazawa 1960), and *Fraxinus mandshurica* var. *japonica*, *Ulmus davidiana*, and *Populus maximowiczii* trees (Yazawa & Ishida 1965). Kano (1987), Miyajima (1992), and Forestry and Forest Products Research Institute (2004) documented the green moisture content for 27 species (14 softwood species and 13 hardwood species), 25 species (9 softwood species and 16 hardwood species), and 15 species (9 softwood species and 6 hardwood species), respectively. However, previous reports were mainly focused on commercial woody species. Thus, data from many woody species are required to determine green moisture content in various woody species growing in Japan. These data should be supplemented with additional information, because green moisture content varies with a number of factors, e.g., seasons, site conditions, geographical locations, inter-tree variation, and intra-tree variation (Gibbs 1958; Yazawa 1960; Forestry and Forest Products Research Institute 2004).

Wood density (or specific gravity) is an important characteristics of wood, which is strongly correlated with physical properties, mechanical properties, burning characteristics, biomass, and carbon stocking (Watanabe 1978; Zobel & van Buitjnen 1989; Zhang 1997; Niklas 1997; Forestry and Forest Products Research Institute 2004). There are many previous investigations of wood density. Basic density data for woody species growing in Japan are summarized and listed in several reports and books (Nakai & Yamai 1982; Forestry and Forest Products Research Institute 2004). However, as with green moisture content, these data were mainly focused on commercial woody species. Data from many wood species are required to determine the basic density of various woody species growing in Japan. These data should be supplemented with additional information, for the same reasons as noted for variability in moisture content (Zobel & van Buitjnen 1989).

We aimed to provide data on green moisture content and basic density for 95 woody species, including three woody lianas, which were investigated in Kyushu University Forests between 2003 and 2006, as part of a project to develop wood properties database.

2 . Materials and methods

Wood samples were collected from three Kyushu University sites, which ranged from warm temperate forest

to cool temperate forest, i.e., Kasuya Research Forest, Shiiba Research Forest, and Ashoro Research Forest (Table 1 and Fig.1).



Fig.1 Location of sampling site

We sampled two to four trees for each of 95 species from three sites, comprised of five softwood species and 90 hardwood species. A total of 204 trees were cut down during July and August between 2003 and 2006, i.e., 35 species in Kasuya Research Forest, 58 species in Shiiba Research Forest, and nine species in Ashoro Research Forest. Table 2 shows species name, age, height, and diameter at breast height (DBH) for the trees sampled. DBH, tree height, and tree age ranged from 1 cm to 10 cm, 2 m to 12 m, and one year to 123 years, respectively.

We cut a short log (about 20 cm length) at breast height from each sample tree and vaseline was applied immediately to the cut sections at both ends, to prevent desiccation. Logs were wrapped in plastic and taken to the laboratory. A wood disc (3 cm thickness) was cut from the middle of each log immediately samples arrived in the laboratory. A wedge spanning from pith to bark was removed from the wood disc. The wedge was separated into inner sapwood and outer sapwood. If the wedge contained colored heartwood, it was separated into heartwood and sapwood based on visual demarcation. The heartwood and sapwood blocks were then separated into inner and outer sections. We did not separate the intermediate wood, which was usually recognized as a pale colored zone between the sapwood and heartwood. If heartwood was found in the stem, we regarded heartwood and sapwood as corewood and outerwood, respectively. When heartwood was not present in the stem, inner sapwood and outer sapwood were regarded as corewood

Table 1 Description of sampling sites.

	Kasuya Research Forest	Shiiba Research Forest	Ashoro Research Forest
Forest area	481 ha	2916 ha	3713 ha
Latitude	33° 38'N	32° 22'N	43° 14'N
Longitude	130° 31'E	131° 08'E	143° 33'E
Altitude	30 m - 553 m	650 m - 1607 m	100 m – 450 m
Annual average temperature	16.2°C	12.9°C	6.0°C
Warmth Index	134.9	101.6	60.0
Annual average precipitatic	1599 mm	3356 mm	749 mm
Forest type*	WTF	ITF	CTF

*WTF: warm temperate forest, ITF: intermediate temperate forest, CTF: cool temperate forest

and outerwood, respectively. We measured the green weight and volume of each block were measured before reweighting after drying the blocks in a 105 °C oven until constant weight. Green volume was determined by the water displacement method.

Green moisture content (GMC) was calculated using formula 1.

$$\text{GMC}(\%) = \frac{\text{Green weight}(\text{g}) - \text{Over dry weight}(\text{g})}{\text{Oven dry weight}(\text{g})} \times 100 \quad (1)$$

Basic density (BD) was calculated using formula 2.

$$\text{BD}(\text{kg}/\text{m}^3) = \frac{\text{Oven dry weight}(\text{kg})}{\text{Green volume}(\text{m}^3)} \quad (2)$$

3 . Results and discussion

Table 3 shows the green moisture content and basic density values of heartwood and sapwood for each sample tree.

3. 1. Green moisture content

Average green moisture content for heartwood in softwood species ranged from 28% in *Chamaecyparis obtusa* to 67% in *Abies firma*. The minimum and maximum values for individual trees were 28% in *Chamaecyparis obtuse* (tree nos. 3 & 4) and 95% in *Abies firma* (tree no. 2), respectively. Average green moisture content for sapwood ranged from 75% in *Tsuga sieboldii* to 160% in *Cryptomeria japonica*. The minimum and maximum values for individual tree were 28% in *Tsuga sieboldii* (tree no. 14) and 202% in *Cryptomeria japonica* (tree no. 8).

It is well known that the green moisture content of softwood species is generally high in sapwood and low in heartwood (e.g. Fushitani *et al.* 1989). However the heartwood of some species also has high moisture content, including *Cryptomeria japonica* and *Abies sachalinensis* (Kano 1987; Kawazumi *et al.* 1991; Nakada *et al.* 1999; Forestry and Forest Products Research Institute 2004; Nakada 2006). Our study found that the green moisture content of sapwood was higher than that of heartwood in all softwood trees. The heartwood of *Abies firma* (tree no.2) had a higher moisture content than all other softwood trees.

Our study also showed that the green moisture content of outer sapwood was higher than that of inner sapwood in all softwood trees. This result may be attributable to intermediate wood, because we did not separate intermediate wood from the sapwood and heartwood. Further investigations testing the separation of intermediate wood from sapwood and heartwood are required.

Only 25 tree samples from 12 hardwood species contained heartwood. Average green moisture content in heartwood ranged from 34% of *Euonymus alatus* f. *striatus* to 83% in *Quercus crispula*. The minimum and maximum values for individual tree were 30% in *Rhus javanica* var. *roxburghii* (tree no.57) and 90% in *Kalopanax pictus* (tree no.32). Average green moisture content of sapwood ranged from 45% in *Fraxinus sieboldiana* to 153% in *Actinidia polygama*. The minimum and maximum values for individual trees were 45% in *Fraxinus sieboldiana* (tree no.27) and 159% in *Actinidia polygama* (tree no.15).

The difference in green moisture content between the heartwood and sapwood was relatively small in hardwood species (2% to 46%) compared with softwood species (31% to 95%). This result agreed with previous reports (Kano

1987; Fushitani *et al.* 1989).

Yazawa *et al.* (1965) studied radial variation in green moisture content in the stem of nine hardwood species and reported three types of distribution pattern. In the first type, the moisture content was higher in the heartwood than sapwood. In the second type, the moisture content was higher in the sapwood than in heartwood. In the third type, only small differences in moisture contents were detected in the sapwood and heartwood. We found the following species belong to the first type: *Castanea crenata*, *Fraxinus mandshurica* var. *japonica*, *Kalopanax pictus*, *Maackia amurensis* subsp. *buengeri*, *Phellodendron amurense*, and *Quercus crispula*. *Rhus javanica* var. *roxburghii* and *Euonymus alatus* f. *striatus* were of the second type, whereas *Morus australis* belonged to the third type. The attribution of *Fraxinus mandshurica* var. *japonica* to type 1 agreed with the results of Yazawa *et al.* (1965), but our classification of *Morus australis* as type 3 was not agreement.

The outer sapwood had a higher green moisture content than the inner sapwood in the majority of the 173 hardwood trees tested. This finding may be attributed to the fact that the region involved in water transport does not include the entire sapwood in broad-leaved species (Umebayashi *et al.* 2007; 2010).

Our study was limited by the short sampling season (July to August) and limits on sampling, i.e., low sample number per species, small tree size, and restriction of tree sampling mainly to Kasuya Forest and Shiiba Forest. Further green moisture content data collection is required.

3. 2. Basic density

The basic density of whole stems showed large interspecies variations, especially in hardwood species. In softwood species, the mean basic density ranged from 378 kg/m³ in *Cryptomeria japonica* to 524 kg/m³ in *Tsuga sieboldii*. The minimum and maximum values for individual trees were 326 kg/m³ in *Cryptomeria japonica* (tree no. 8) and 536 kg/m³ in *Tsuga sieboldii* (tree no. 13). In contrast, the mean basic density of hardwood species ranged from 266 kg/m³ in *Paulownia tomentosa* to 725 kg/m³ in *Rhaphiolepis indica* var. *umbellata*. The minimum and maximum values for individual trees were 251 kg/m³ in

Zanthoxylum ailanthoides (tree no. 191) and 751 kg/m³ in *Rhaphiolepis indica* var. *umbellata* (tree no. 163).

Numerous reports indicate that basic density varies with radial variations from the pith to bark in the stem of woody species (Fushitani *et al.* 1989; Zobel & Sprague 1998). In all but one of softwood trees (tree no.1), basic density tended to decrease from corewood to outerwood. We observed three types of radial variation patterns in the basic density of hardwood species. In the first type, basic density was higher in corewood than outerwood (e.g., *Kalopanax pictus* and *Maackia amurensis* subsp. *buengeri*). In the second type, basic density was higher in outerwood than corewood (e.g., *Betula grossa* and *Litsea acuminata*). Only small differences in the basic density of corewood and outerwood were detected in the third type (e.g., *Magnolia obovata* and *Dendropanax trifidus*). Further basic density data are required to determine radial variation patterns for each species.

3. 3. Information on the age and size of heartwood formation

It is well known that heartwood formation begins after trees reach a certain age or size (Watanabe 1978). However, there is little information on the starting size and age of heartwood formation for woody species growing in Japan. We derived data on the age and size of heartwood formation from the presence or absence of heartwood (Table 3), tree age and DBH (Table 2). Heartwood was observed in the stems of three species of five softwood species (16 trees) and 12 of 90 hardwood species (26 trees). Among the softwood species, the smallest size and ring number (cambial age) for a stem containing heartwood was 6 cm and seven growth rings in *Chamaecyparis obtuse* (tree no. 3). Among the hardwood species, this was 4 cm in *Euonymus alatus* f. *striatus* (tree no. 104) and seven growth rings in *Rhus javanica* var. *roxburghii* (tree nos.55, 56 and 57). In contrast, the largest size and ring number for a hardwood species stem containing no heartwood was 9 cm in *Chamaecyparis obtuse* (trees no. 6) and 11 growth rings in *Pinus densiflora* (tree no.11), whereas among the hardwood species, this was 10 cm in *Ilex crenata* var. *fukasawana* (tree no.120) and 80 growth rings in *Fraxinus sieboldiana* (tree no.27).

Table 2 Description of sample trees.

Japanese common name (Scientific name)	Tree no.	Tree age (year)	DBH (cm)	Tree height (m)	Sampling date	Sampling site*	Japanese common name (Scientific name)	Tree no.	Tree age (year)	DBH (cm)	Tree height (m)	Sampling date	Sampling site*
Softwood													
Momi (<i>Abies firma</i>)	1	69	8.9	7.8	2004/7/16	S	Nogurumi (<i>Platanus sibirica</i>)	43	4	3.0	3.8	2005/8/8	K
Hinoaki (<i>Chamaecyparis obtusa</i>)	2	26	9.0	5.9	2004/7/16	S		44	5	2.5	3.7	2005/8/8	K
	3	8	6.2	4.7	2005/8/30	S	Kumagi (<i>Quercus acutissima</i>)	45	20	6.8	7.6	2003/8/19	S
	4	7	5.7	4.1	2005/8/30	S		46	20	7.3	6.2	2003/8/19	S
	5	10	7.5	5.6	2005/8/26	K	Abemaki (<i>Quercus variabilis</i>)	47	18	6.8	7.5	2003/8/19	S
	6	10	8.6	6.0	2005/8/26	K		48	20	9.3	8.2	2003/8/19	S
Sugi (<i>Cryptomeria japonica</i>)	7	5	2.8	3.3	2005/8/25	S		49	22	6.5	6.1	2005/8/10	K
	8	8	3.7	4.7	2005/8/25	S	Mizunara (<i>Quercus crispula</i>)	50	16	5.5	4.4	2005/8/10	K
	9	10	3.5	4.1	2005/8/26	K		51	27	7.0	9.2	2003/8/22	S
	10	10	8.1	5.9	2005/8/26	K		52	23	5.5	8.8	2003/8/22	S
Akamatsu (<i>Pinus densiflora</i>)	11	11	4.6	4.4	2004/8/24	S		53	44	9.8	11.1	2004/8/12	A
	12	9	4.8	4.2	2004/8/24	S		54	41	9.7	8.8	2004/8/12	A
Tsuga (<i>Tsuga sieboldii</i>)	13	76	7.5	7.3	2004/8/24	S	Nurude (<i>Rhus javanica</i> var. <i>rosburghii</i>)	55	7	6.4	5.1	2004/8/31	S
	14	76	8.2	10.0	2004/8/24	S		56	7	6.4	7.8	2004/8/31	S
Hardwood													
Ring-porous wood													
Mataabi (<i>Actinidia polygama</i>)	15	12	1.9	8.3	2004/7/16	S	Yamanushi (<i>Toxicodendron trichocarpum</i>)	59	33	4.7	4.7	2004/8/7	A
	16	9	2.0	10.9	2004/7/16	S		60	43	6.4	6.0	2004/8/7	A
Urinoki (<i>Alangium platanifolium</i> var. <i>trilobum</i>)	17	22	2.3	4.4	2003/8/10	S		61	10	5.8	9.4	2004/8/31	S
	18	25	4.4	7.3	2003/8/10	S	Kurozuru (<i>Tripteris yunnanensis</i>)	62	11	6.4	7.9	2004/8/31	S
Taranoki (<i>Aralia elata</i>)	19	4	3.5	2.8	2004/7/16	S	Yamafuji (<i>Wisteria brachybotrys</i>)	63	19	2.5	9.2	2003/7/25	S
	20	4	4.9	2.7	2004/7/16	S		64	22	3.5	11.5	2003/7/25	S
Kuri (<i>Castanea crenata</i>)	21	20	5.8	6.9	2005/8/22	K	Inuzansho (<i>Zanthoxylum schinifolium</i>)	65	7	3.3	4.8	2004/7/7	S
	22	18	5.7	4.1	2005/8/22	K		66	10	2.5	4.5	2004/7/7	S
Aodama (<i>Fraxinus lanuginosa</i> f. <i>serrata</i>)	23	23	5.7	5.8	2004/8/9	A	Semi-ring-porous wood						
	24	35	6.0	8.1	2004/8/9	A	Kakuremino (<i>Dendropanax trifidus</i>)	67	23	3.5	5.1	2006/7/28	K
Yachidamo (<i>Fraxinus mandshurica</i> var. <i>japonica</i>)	25	22	6.4	7.8	2003/8/13	A		68	36	5.5	6.8	2006/7/28	K
	26	10	4.9	8.7	2003/8/13	A	Navashirogumi (<i>Elaeagnus pungens</i>)	69	10	4.7	5.2	2005/8/16	K
Marubaodamo (<i>Fraxinus sieboldiana</i>)	27	80	7.5	11.1	2003/8/31	S		70	9	1.1	2.2	2005/8/16	K
	28	34	4.7	10.2	2003/8/31	S	Diffuse-porous wood						
Hatigiri (<i>Katopanax pictus</i>)	29	60	5.8	5.8	2003/8/25	S	Chidormoki (<i>Acer carpinifolium</i>)	71	26	6.0	5.5	2003/8/22	S
	30	15	4.7	4.9	2003/8/25	S		72	21	5.6	6.1	2003/8/22	S
	31	48	9.7	11.5	2004/8/12	A	Irohantomiji (<i>Acer palmatum</i>)	73	31	4.5	5.3	2003/7/30	S
	32	69	8.3	10.3	2004/8/12	A		74	23	3.3	3.5	2003/7/30	S
Inuejyu (<i>Maackia amurensis</i> subsp. <i>buergeri</i>)	33	51	7.9	7.4	2004/8/12	A	Itayakaede (<i>Acer pictum</i> subsp. <i>dissectum</i>)	75	29	7.2	5.9	2003/7/31	S
	34	52	9.8	8.7	2004/8/12	A		76	33	7.2	7.0	2003/7/31	S
Yamagawa (<i>Morus australis</i>)	35	48	5.4	7.5	2004/8/25	S	Ezotaya (<i>Acer pictum</i> subsp. <i>mono</i> f. <i>mono</i>)	77	28	6.2	8.2	2004/8/11	A
	36	33	5.5	7.4	2004/8/25	S		78	32	6.8	9.4	2004/8/11	A
Kiri (<i>Paulownia tomentosa</i>)	37	1	4.2	5.5	2005/8/17	K	Enkoukaede (<i>Acer pictum</i> subsp. <i>dissectum</i> f. <i>dissectum</i>)	79	21	7.6	6.6	2003/8/1	S
	38	3	5.1	5.0	2005/8/17	K		80	15	6.8	5.5	2003/8/1	S
Kihada (<i>Phellodendron amurense</i>)	39	21	9.4	8.3	2004/7/16	S	Kohauchiwakaede (<i>Acer sieboldianum</i>)	81	57	9.7	9.4	2003/7/22	S
	40	19	8.6	6.5	2004/7/16	S		82	54	9.0	6.8	2003/7/22	S
Kobamoki (<i>Phyllanthus flexuosus</i>)	41	9	3.9	2.3	2005/8/30	K	Yashabushi (<i>Ahims firma</i>)	83	5	2.9	4.0	2005/8/28	K
	42	9	2.4	2.4	2005/8/30	K		84	8	6.8	5.0	2005/8/28	K

* S. Shiiba Research Forest, K. Kasuya Research Forest, A. Ashoro Research Forest

Table 2 (Continued)

Diffuse-porous wood				Diffuse-porous wood									
Japanese common name (Scientific name)	Tree no.	Tree age (year)	DBH (cm)	Tree height (m)	Sampling date	Sampling site*	Japanese common name (Scientific name)	Tree no.	Tree age (year)	DBH (cm)	Tree height (m)	Sampling date	Sampling site*
Mukunoki (<i>Aphananthe aspera</i>)	85	12	1.8	4.3	2005/7/19	K	Nezumimochi (<i>Ligustrum japonicum</i>)	129	26	3.0	3.3	2005/8/23	K
Mizume (<i>Betula grossa</i>)	86	10	5.5	5.6	2005/7/19	K	Kanakugimochi (<i>Lindera erythrocarpa</i>)	130	29	2.5	3.2	2005/8/23	K
Yabutsubaki (<i>Camellia japonica</i>)	87	23	8.6	9.5	2003/8/22	S	Aburachan (<i>Lindera praecox</i>)	131	21	5.6	7.0	2003/8/4	S
Akashide (<i>Carpinus laeiflora</i>)	88	20	6.8	8.0	2003/8/22	S	Shitromoji (<i>Lindera triloba</i>)	132	29	9.7	6.3	2003/8/4	S
Inushide (<i>Carpinus ischonoki</i>)	89	61	7.8	6.0	2003/8/22	S	Baribarimochi (<i>Litsea acuminata</i>)	133	14	3.8	5.5	2003/8/1	S
Isunoki (<i>Distylium racemosum</i>)	90	33	5.0	5.8	2003/8/22	S	Kagonoki (<i>Litsea coreana</i>)	134	19	2.6	4.0	2003/8/1	S
Yamagaki (<i>Diospyros kaki</i> var. <i>sihvestris</i>)	91	15	2.6	3.4	2005/8/28	K	Tabunoki (<i>Machilus thunbergii</i>)	135	27	6.0	6.9	2003/8/9	S
Utsugi (<i>Denzitia crenata</i>)	92	18	2.3	3.3	2005/8/28	K	Hoonoki (<i>Magnolia obovata</i>)	136	15	2.9	5.2	2003/8/9	S
Komayumi (<i>Eriomyium alatum</i> f. <i>striatum</i>)	93	11	4.9	6.6	2003/8/27	S	Tamushiba (<i>Magnolia salicifolia</i>)	137	15	3.8	4.9	2005/7/19	K
Fusazakura (<i>Euphelia polyantha</i>)	94	10	5.1	5.4	2003/8/27	S	Awabuki (<i>Meliosma myriantha</i>)	138	15	3.8	4.8	2005/7/19	K
Hisakaki (<i>Eurya japonica</i>)	95	11	5.0	6.9	2003/8/27	S	Shirodamo (<i>Neolitsea sericea</i>)	139	9	2.8	3.2	2005/8/6	K
Buna (<i>Fagus crenata</i>)	96	10	5.0	4.6	2003/8/27	S	Asebi (<i>Pteris japonica</i>)	140	9	3.1	4.1	2005/8/6	K
Inubuna (<i>Fagus japonica</i>)	97	14	3.9	6.2	2005/8/27	K	Tobera (<i>Pitosporum tobrera</i>)	141	13	4.1	4.7	2006/8/3	K
Hosobainubwa (<i>Ficus erecta</i> f. <i>sieboldii</i>)	98	14	3.3	5.5	2005/8/27	K	Yamanarashi (<i>Populus sieboldii</i>)	142	12	3.6	3.5	2006/8/3	K
Nanaminoki (<i>Ilex chinensis</i>)	99	9	4.9	6.5	2005/8/18	K	Kamatsuka (<i>Pourthiaca villosa</i> var. <i>laevis</i>)	143	17	4.8	5.8	2003/8/28	S
Inutsuge (<i>Ilex crenata</i>)	100	9	4.1	4.9	2005/8/18	K	Asagara (<i>Pterosyrax corymbosa</i>)	144	17	5.0	5.4	2003/8/28	S
Tsukushinutsuge (<i>Ilex crenata</i> var. <i>fhakasanana</i>)	101	7	2.5	4.2	2004/8/22	S	Sharinbai (<i>Rhaphiolepis indica</i> var. <i>umbellata</i>)	145	16	4.0	5.2	2003/8/6	S
Soyogo (<i>Ilex pedunculosa</i>)	102	9	2.9	4.3	2004/8/22	S	Nekoyanagi (<i>Salix gracilistyla</i>)	146	16	6.3	5.7	2003/8/6	S
Kuroganemochi (<i>Ilex rotunda</i>)	103	57	6.4	5.1	2004/7/16	S	Yamayayagi (<i>Salix sieboldiana</i>)	147	16	6.9	6.5	2003/8/4	S
Inuumemodoki (<i>Ilex serrata</i> f. <i>argutaideans</i>)	104	43	4.0	5.0	2004/7/16	S	Shiraki (<i>Sapium japonicum</i>)	148	23	7.5	6.0	2003/8/4	S
Shikimi (<i>Ulicium anisatum</i>)	105	11	4.0	7.3	2003/8/6	S	Nankinnamakamado (<i>Sorbus gracilis</i>)	149	29	8.5	6.2	2003/8/20	S
	106	17	4.1	7.4	2003/8/6	S		150	28	8.5	5.9	2003/8/20	S
	107	28	3.9	3.3	2005/8/11	K		151	8	2.6	3.2	2005/8/25	K
	108	25	2.2	3.6	2005/8/11	K		152	7	3.9	3.3	2005/8/25	K
	109	19	5.5	6.3	2003/8/19	S		153	9	5.3	5.4	2003/8/5	S
	110	24	6.4	8.2	2003/8/19	S		154	10	6.2	5.4	2003/8/5	S
	111	16	5.6	5.6	2003/8/5	S		155	8	3.2	4.2	2006/8/9	K
	112	17	5.2	6.4	2003/8/5	S		156	15	5.6	6.0	2006/8/9	K
	113	10	2.5	4.2	2006/7/20	K		157	36	8.6	8.5	2004/8/12	A
	114	9	3.3	4.0	2006/7/20	K		158	30	7.7	7.3	2004/8/12	A
	115	15	3.2	6.0	2006/8/8	K		159	32	7.2	7.0	2003/8/6	S
	116	15	3.4	4.9	2006/8/8	K		160	35	4.5	5.2	2003/8/6	S
	117	10	1.5	2.2	2005/8/13	K		161	21	8.5	6.2	2003/7/25	S
	118	12	2.0	2.7	2005/8/13	K		162	21	5.0	5.1	2003/7/25	S
	119	43	6.6	6.2	2004/7/16	S		163	22	3.1	4.9	2003/8/6	K
	120	51	9.9	6.8	2004/7/16	S		164	30	5.2	6.3	2003/8/6	K
	121	38	5.1	5.0	2003/8/22	S		165	25	6.2	5.2	2004/8/23	S
	122	38	5.0	7.0	2003/8/22	S		166	16	3.3	4.0	2004/8/23	S
	123	10	4.3	4.2	2005/7/22	K		167	22	6.0	5.6	2003/8/30	S
	124	11	5.8	3.5	2005/7/22	K		168	23	3.9	4.1	2003/8/30	S
	125	41	3.0	4.1	2004/8/27	S		169	17	4.2	6.2	2003/7/31	S
	126	34	2.2	3.8	2004/8/27	S		170	9	3.7	3.9	2003/7/31	S
	127	18	3.6	3.7	2003/8/22	S		171	29	1.8	4.9	2003/8/22	S
	128	45	4.6	3.5	2003/8/22	S		172	26	2.0	5.8	2003/8/22	S

Table 2 (Continued)

Japanese common name (Scientific name)	Tree no.	Tree age (year)	DBH (cm)	Tree height (m)	Sampling date	Sampling site*	Japanese common name (Scientific name)	Tree no.	Tree age (year)	DBH (cm)	Tree height (m)	Sampling date	Sampling site*
Diffuse-porous wood							Diffuse-porous wood						
Himeshara (<i>Stewartia monadelpha</i>)	173	21	6.4	6.1	2003/8/19	S	Karasuzanshou (<i>Zanthoxylum ailanthoides</i>)	191	10	6.8	4.1	2005/8/8	K
Egonoki (<i>Syrax japonica</i>)	174	28	5.8	5.8	2003/8/19	S	Fuyuzanshou (<i>Zanthoxylum armatum</i> var. <i>subrifoliatum</i>)	192	3	5.1	3.7	2005/8/8	K
Kohakuumboku (<i>Syrax shiratanu</i>)	175	22	5.5	5.5	2003/8/23	S		193	9	4.0	3.8	2006/8/5	K
	176	22	6.2	5.8	2003/8/23	S		194	13	3.0	4.6	2006/8/5	K
	177	7	2.9	3.8	2004/7/7	S	Radial-porous wood						
	178	9	3.7	5.8	2004/7/7	S	Sudajii (<i>Castanopsis sieboldii</i>)	195	22	5.0	4.6	2005/8/27	K
	179	21	3.7	5.7	2006/7/31	K		196	18	3.3	3.6	2005/8/27	K
	180	14	2.2	3.7	2006/7/31	K	Matebashii (<i>Lithocarpus edulis</i>)	197	16	4.0	5.5	2006/8/2	K
	181	6	2.4	2.9	2005/8/13	K		198	16	3.3	5.0	2006/8/2	K
	182	7	2.7	2.8	2005/8/13	K	Arakashi (<i>Quercus glauca</i>)	199	13	6.2	7.6	2005/8/6	K
	183	11	3.7	4.4	2003/8/25	S		200	8	5.0	6.3	2005/8/6	K
	184	11	7.4	5.2	2003/8/25	S	Shirakashi (<i>Quercus myrsinaefolia</i>)	201	16	2.9	5.5	2006/8/9	K
	185	34	6.5	7.4	2004/8/11	A		202	23	5.9	6.7	2006/8/9	K
	186	30	6.0	7.8	2004/8/11	A	Urajirogashi (<i>Quercus salicina</i>)	203	24	7.4	7.0	2004/7/16	S
	187	18	3.2	4.1	2006/7/29	K		204	9	3.5	5.4	2004/7/16	S
	188	22	4.1	3.3	2006/7/29	K	Wood vesselless						
	189	23	4.0	5.3	2004/7/16	S	Yamaguruma (<i>Trochodendron aralioides</i>)	205	85	6.8	5.8	2003/8/22	S
	190	27	3.9	5.3	2004/7/16	S		206	123	7.0	4.8	2003/8/22	S

Table 3 Green moisture content and basic density (kg/m³) of the trees. (- No observation of heartwood)

Tree no.	Japanese common name (Scientific name)	Green moisture content (%)						Basic density (kg/m ³)							
		Heartwood			Sapwood			Heartwood			Sapwood				
		Inner	Outer	All	Inner	Outer	All	Inner	Outer	All	Inner	Outer	All		
Softwood															
1	Monii (<i>Abies firma</i>)	42	35	39	43	113	84	61	453	422	438	492	473	481	458
2	115	75	95	155	181	167	152	373	356	364	337	309	323	331	
AVG	79	55	67	99	147	126	106	413	389	401	415	391	402	394	
3	32	26	28	100	148	123	78	481	489	486	460	446	453	468	
4	36	24	28	92	135	115	81	501	503	502	467	401	430	456	
5	-	-	-	109	162	131	131	-	-	-	458	387	426	426	
6	-	-	-	123	155	138	138	-	-	-	458	398	428	428	
AVG	34	25	28	106	150	127	107	491	496	494	461	408	434	444	
7	-	-	-	123	200	154	154	-	-	-	444	331	391	391	
8	-	-	-	162	247	202	202	-	-	-	357	297	326	326	
9	-	-	-	116	206	154	154	-	-	-	427	321	375	375	
10	-	-	-	122	142	131	131	-	-	-	444	394	420	420	
AVG	-	-	-	131	199	160	160	-	-	-	418	336	378	378	
11	-	-	-	152	169	160	160	-	-	-	397	372	385	385	
12	-	-	-	121	159	139	139	-	-	-	411	369	390	390	
AVG	-	-	-	137	164	150	150	-	-	-	404	371	387	387	
13	58	47	53	60	108	83	64	600	540	569	532	452	491	536	
14	30	32	31	32	97	66	46	563	498	534	503	471	486	513	
AVG	44	39	42	46	103	75	55	581	519	552	518	461	488	524	
Hardwood															
Ring-porous wood															
15	-	-	-	116	206	159	159	-	-	-	463	310	374	374	
16	-	-	-	100	192	146	146	-	-	-	414	316	358	358	
AVG	-	-	-	108	199	153	153	-	-	-	439	313	366	366	
17	-	-	-	58	59	58	58	-	-	-	648	605	627	627	
18	-	-	-	50	59	55	55	-	-	-	567	551	558	558	
AVG	-	-	-	54	59	57	57	-	-	-	607	578	593	593	
19	-	-	-	86	113	105	105	-	-	-	183	455	322	322	
20	-	-	-	48	65	60	60	-	-	-	184	402	304	304	
AVG	-	-	-	67	89	83	83	-	-	-	184	428	313	313	
21	71	85	78	83	87	85	82	502	493	498	484	495	490	494	
22	66	79	73	84	101	93	83	517	513	515	495	463	479	496	
AVG	69	82	75	83	94	89	82	509	503	506	490	479	485	495	
23	-	-	-	49	63	57	57	-	-	-	622	604	612	612	
24	-	-	-	49	56	53	53	-	-	-	640	610	625	625	
AVG	-	-	-	49	60	55	55	-	-	-	631	607	619	619	
25	72	87	80	45	66	56	68	502	486	493	487	479	483	488	
26	74	89	82	49	70	61	72	609	613	611	616	547	575	591	
AVG	73	88	81	47	68	58	70	555	550	552	552	513	529	539	
27	-	-	-	43	46	45	45	-	-	-	608	627	618	618	
28	-	-	-	42	50	46	46	-	-	-	597	599	598	598	
AVG	-	-	-	43	48	45	45	-	-	-	602	613	608	608	
29	77	75	76	58	95	79	77	498	506	502	525	405	451	474	
30	-	-	-	67	115	90	90	-	-	-	558	408	474	474	
31	57	67	62	86	101	94	76	540	538	539	481	394	431	485	
32	80	99	90	92	102	98	92	498	465	481	389	313	342	456	
AVG	72	80	76	76	103	90	84	512	503	507	488	380	424	467	
33	29	64	46	85	92	90	53	567	533	550	453	424	429	528	
34	63	80	71	89	97	95	75	585	545	565	466	471	470	546	
AVG	46	72	59	87	94	93	64	576	539	558	460	447	450	537	
Ring-porous wood															
35	68	69	69	65	76	71	70	594	600	597	582	569	574	584	
36	81	72	76	54	95	75	76	613	580	595	498	486	492	540	
AVG	75	71	73	59	85	73	73	603	590	596	540	527	533	562	
37	-	-	-	68	113	91	91	-	-	-	244	283	263	263	
38	-	-	-	72	142	107	107	-	-	-	260	275	269	269	
AVG	-	-	-	70	127	99	99	-	-	-	252	279	266	266	
39	51	63	57	67	101	87	68	377	398	387	446	378	403	393	
40	42	42	42	43	77	61	48	397	467	433	423	388	403	423	
AVG	46	53	50	55	89	74	58	387	433	410	434	383	403	408	
41	-	-	-	60	76	68	68	-	-	-	715	624	668	668	
42	-	-	-	57	73	64	64	-	-	-	752	640	708	708	
AVG	-	-	-	58	75	66	66	-	-	-	733	632	688	688	
43	-	-	-	94	116	105	105	-	-	-	415	442	429	429	
44	-	-	-	84	101	93	93	-	-	-	473	486	480	480	
AVG	-	-	-	89	109	99	99	-	-	-	444	464	455	455	
45	-	-	-	72	70	71	71	-	-	-	659	615	635	635	
46	-	-	-	65	70	68	68	-	-	-	628	611	619	619	
AVG	-	-	-	69	70	69	69	-	-	-	644	613	627	627	
47	-	-	-	84	83	84	84	-	-	-	626	564	593	593	
48	-	-	-	84	113	97	97	-	-	-	649	509	579	579	
49	-	-	-	70	74	72	72	-	-	-	659	646	652	652	
50	-	-	-	70	79	74	74	-	-	-	685	645	663	663	
AVG	-	-	-	77	87	82	82	-	-	-	655	591	622	622	
51	-	-	-	75	85	81	81	-	-	-	579	566	572	572	
52	-	-	-	67	72	69	69	-	-	-	638	565	600	600	
53	80	82	81	67	60	63	74	634	630	632	596	537	558	600	
54	83	87	85	65	71	68	78	649	647	648	598	527	555	607	
AVG	82	84	83	68	72	70	75	641	639	640	603	549	571	594	
55	67	57	62	72	122	99	80	371	361	366	365	372	369	367	
56	67	71	69	89	136	111	86	377	452	416	488	272	356	390	
57	36	24	30	40	113	76	76	410	420	415	472	426	450	450	
58	35	29	32	31	99	72	72	419	452	432	460	407	427	427	
AVG	51	45	48	58	117	90	78	394	421	407	446	369	401	409	
59	46	41	43	60	83	73	53	422	484	455	434	472	454	455	
60	51	56	53	50	85	68	59	535	542	539	521	476	496	523	
AVG	48	48	48	55	84	70	56	479	513	497	478	474	475	489	
61	-	-	-	129	129	129	129	-	-	-	630	375	482	482	
62	-	-	-	77	136	101	101	-	-	-	656	412	528	528	
AVG	-	-	-	103	132	115	115	-	-	-	643	393	505	505	
63	-	-	-	121	204	149	149	-	-	-	394	265	338	338	
64	-	-	-	100	173	136	136	-	-	-	380	307	357	357	
AVG	-	-	-	111	188	143	143	-	-	-	387	301	347	347	
65	-	-	-	40	63	52	52	-	-	-	567	544	555	555	
66	-	-	-	40	52	46	46	-	-	-	560	551	555	555	
AVG	-	-	-	40	57	49	49	-	-	-	563	547	555	555	
Semi ring porous wood															
67	-	-	-	72	93	83	83	-	-	-	481	488	486	486	
68	-	-	-	75	100	87	87	-	-	-	431	428	430	430	
AVG	-	-	-	74	96	85	85	-	-	-	456	458	458	458	

Table 3 (Continued)

Tree no.	Japanese common name (Scientific name)	Green moisture content (%)						Basic density (kg/m ³)							
		Heartwood			Sapwood			Heartwood			Sapwood				
		Inner	Outer	All	Inner	Outer	All	Inner	Outer	All	Inner	Outer	All		
Semi ring porous wood															
69	Navasirugumi (<i>Elaeagnus pungens</i>)	-	-	-	61	74	68	68	-	-	-	710	646	677	677
70	AVG	-	-	-	59	72	64	64	-	-	-	627	592	612	612
71	Chidoroaki (<i>Acer carpinifolium</i>)	-	-	-	60	73	66	66	-	-	-	668	619	644	644
72	AVG	-	-	-	71	82	77	77	-	-	-	453	483	468	468
73	Irohomonji (<i>Acer palmatum</i>)	-	-	-	75	83	79	79	-	-	-	455	491	475	475
74	AVG	-	-	-	53	62	57	57	-	-	-	454	487	471	471
75	Itayakaede (<i>Acer pictum</i> subsp. <i>dissectum</i>)	-	-	-	52	63	58	58	-	-	-	502	538	521	521
76	AVG	-	-	-	53	63	58	58	-	-	-	512	538	525	525
77	Ezoitaya (<i>Acer pictum</i> subsp. <i>dissectum</i>)	-	-	-	65	89	77	77	-	-	-	423	462	442	442
78	AVG	-	-	-	61	72	66	66	-	-	-	463	489	476	476
79	Enkoukaede (<i>Acer pictum</i> subsp. <i>dissectum</i>)	-	-	-	63	80	72	72	-	-	-	443	476	459	459
80	AVG	-	-	-	54	60	57	57	-	-	-	548	583	565	565
81	Kohauchikwaede (<i>Acer sieboldianum</i>)	-	-	-	56	69	63	63	-	-	-	548	541	544	544
82	AVG	-	-	-	55	65	60	60	-	-	-	548	562	555	555
83	Yashubashi (<i>Alnus firma</i>)	-	-	-	49	61	54	54	-	-	-	613	586	600	600
84	AVG	-	-	-	50	60	55	55	-	-	-	557	590	573	573
85	Mukunoki (<i>Aphananthe aspera</i>)	-	-	-	49	61	55	55	-	-	-	585	588	586	586
86	AVG	-	-	-	57	64	60	60	-	-	-	541	580	559	559
87	Mizame (<i>Betula grossa</i>)	-	-	-	63	60	61	61	-	-	-	493	560	528	528
88	AVG	-	-	-	60	62	61	61	-	-	-	517	570	544	544
89	Yabusubashi (<i>Camellia japonica</i>)	-	-	-	72	82	78	78	-	-	-	448	459	454	454
90	AVG	-	-	-	75	70	72	72	-	-	-	494	541	515	515
91	Mukunoki (<i>Aphananthe aspera</i>)	-	-	-	73	76	75	75	-	-	-	471	500	485	485
92	AVG	-	-	-	73	90	83	83	-	-	-	384	462	424	424
93	Mizame (<i>Betula grossa</i>)	-	-	-	63	83	72	72	-	-	-	517	510	514	514
94	AVG	-	-	-	68	87	78	78	-	-	-	450	486	469	469
95	Yabusubashi (<i>Camellia japonica</i>)	-	-	-	71	66	69	69	-	-	-	518	589	548	548
96	AVG	-	-	-	69	69	69	69	-	-	-	508	560	533	533
97	Yabusubashi (<i>Camellia japonica</i>)	-	-	-	77	82	79	79	-	-	-	513	574	540	540
98	AVG	-	-	-	74	73	74	74	-	-	-	631	605	619	619
99	Yabusubashi (<i>Camellia japonica</i>)	-	-	-	71	80	75	75	-	-	-	610	643	626	626
100	AVG	-	-	-	71	68	70	70	-	-	-	631	614	622	622
101	Akashide (<i>Carpinus lasiocarpa</i>)	-	-	-	73	76	74	74	-	-	-	615	656	635	635
102	AVG	-	-	-	88	88	88	88	-	-	-	622	629	626	626
103	Inushide (<i>Carpinus oschonostii</i>)	-	-	-	88	88	88	88	-	-	-	451	488	471	471
104	AVG	-	-	-	88	88	88	88	-	-	-	451	488	471	471
105	Isumoki (<i>Distylium racemosum</i>)	-	-	-	95	95	95	95	-	-	-	449	474	462	462
106	AVG	-	-	-	95	95	95	95	-	-	-	449	474	462	462
107	Yamagaki (<i>Diospyros kads</i> var. <i>syhestris</i>)	-	-	-	76	80	78	78	-	-	-	623	647	634	634
108	AVG	-	-	-	85	89	87	87	-	-	-	624	596	610	610
109	AVG	-	-	-	81	85	83	83	-	-	-	623	621	622	622
110	AVG	-	-	-	63	79	71	71	-	-	-	561	546	553	553
111	AVG	-	-	-	53	57	55	55	-	-	-	587	566	577	577
112	AVG	-	-	-	58	68	63	63	-	-	-	574	556	565	565
Diffuse-porous wood															
101	Utsugi (<i>Dentizia crenata</i>)	-	-	-	93	109	102	102	-	-	-	600	518	549	549
102	AVG	-	-	-	88	94	91	91	-	-	-	587	610	601	601
103	Komayumi (<i>Enonymus alatus</i> f. <i>stratus</i>)	-	-	-	34	33	34	34	-	-	-	718	681	697	697
104	AVG	-	-	-	38	35	34	34	-	-	-	666	700	682	682
105	Fusazakura (<i>Empetrum polyanthum</i>)	-	-	-	36	34	34	34	-	-	-	692	691	689	689
106	AVG	-	-	-	123	90	103	103	-	-	-	494	571	537	537
107	Hisakaki (<i>Eurya japonica</i>)	-	-	-	121	136	128	128	-	-	-	504	461	483	483
108	AVG	-	-	-	122	113	116	116	-	-	-	499	516	510	510
109	Buna (<i>Fagus crenata</i>)	-	-	-	107	109	108	108	-	-	-	524	528	526	526
110	AVG	-	-	-	96	105	101	101	-	-	-	565	528	545	545
111	Inubuna (<i>Fragaria japonica</i>)	-	-	-	101	107	104	104	-	-	-	544	528	535	535
112	AVG	-	-	-	65	75	70	70	-	-	-	528	557	543	543
113	Hosobambiva (<i>Ficus erecta</i> f. <i>sieboldii</i>)	-	-	-	109	112	111	111	-	-	-	504	519	511	511
114	AVG	-	-	-	87	94	90	90	-	-	-	516	538	527	527
115	Nanaminoki (<i>Ilex chinensis</i>)	-	-	-	91	94	93	93	-	-	-	515	551	532	532
116	AVG	-	-	-	89	93	91	91	-	-	-	513	559	538	538
117	Inutsuge (<i>Ilex crenata</i>)	-	-	-	90	94	92	92	-	-	-	514	555	535	535
118	AVG	-	-	-	132	116	123	123	-	-	-	479	536	508	508
119	Tsukushimatsuge (<i>Ilex crenata</i> var. <i>fukusawana</i>)	-	-	-	104	104	104	104	-	-	-	562	529	545	545
120	AVG	-	-	-	118	110	113	113	-	-	-	520	533	527	527
121	Soyogo (<i>Ilex pedunculosa</i>)	-	-	-	91	87	89	89	-	-	-	531	545	539	539
122	AVG	-	-	-	87	94	91	91	-	-	-	578	551	562	562
123	Kiruganenochi (<i>Ilex rotunda</i>)	-	-	-	89	91	90	90	-	-	-	555	548	551	551
124	AVG	-	-	-	63	85	74	74	-	-	-	593	532	562	562
125	Inuamemochi (<i>Ilex serrata</i> f. <i>argenteus</i>)	-	-	-	70	89	79	79	-	-	-	588	512	548	548
126	AVG	-	-	-	67	87	76	76	-	-	-	590	522	555	555
127	Shikimi (<i>Illicium anisatum</i>)	-	-	-	66	75	71	71	-	-	-	655	608	629	629
128	AVG	-	-	-	58	63	60	60	-	-	-	704	646	675	675
129	Nezumimochi (<i>Uegostrium japonicum</i>)	-	-	-	62	69	66	66	-	-	-	679	627	652	652
130	AVG	-	-	-	75	89	82	82	-	-	-	571	558	565	565
131	Kanaginoki (<i>Linum erythrorhizon</i>)	-	-	-	53	72	62	62	-	-	-	673	614	645	645
132	AVG	-	-	-	64	80	72	72	-	-	-	622	586	605	605
133	AVG	-	-	-	94	119	110	110	-	-	-	531	474	499	499
134	AVG	-	-	-	99	105	100	100	-	-	-	544	512	528	528
135	AVG	-	-	-	97	112	105	105	-	-	-	538	493	513	513
136	AVG	-	-	-	63	137	88	88	-	-	-	515	446	489	489
137	AVG	-	-	-	85	98	91	91	-	-	-	438	545	488	488
138	AVG	-	-	-	74	117	89	89	-	-	-	476	496	489	489
139	AVG	-	-	-	89	130	106	106	-	-	-	563	472	520	520
140	AVG	-	-	-	80	109	94	94	-	-	-	616	532	574	574
141	AVG	-	-	-	85	119	100	100	-	-	-	589	502	547	547
142	AVG	-	-	-	61	63	62	62	-	-	-	671	646	659	659
143	AVG	-	-	-	61	60	60	60	-	-	-	662	647	654	654
144	AVG	-	-	-	61	62	61	61	-	-	-	667	646	657	657
145	AVG	-	-	-	65	88	77	77	-	-	-	438	448	443	443
146	AVG	-	-	-	76	111	93	81	-	-	-	451	508	461	461
147	AVG	-	-	-	66	66	66	66	-	-	-	468	451	473	473
148	AVG	-	-	-	70	99	85	85	-	-	-	454	463	455	455

Table 3 (Continued)

Japanese common name (Scientific name)	Tree no.	Green moisture content (%)						Basic density (kg/m ³)											
		Heartwood			Sapwood			Heartwood			Sapwood								
		Inner	Outer	All	Inner	Outer	All	Inner	Outer	All	Inner	Outer	All						
Diffuse-porous wood																			
Inubuna (<i>Fagus japonica</i>)	111	-	-	91	94	93	93	-	-	515	551	532	532	-	-	520	511	515	515
	112	-	-	89	93	91	91	-	-	513	559	538	538	-	-	491	509	501	501
AVG		-	-	90	94	92	92	-	-	514	555	535	535	-	-	506	510	508	508
Hosobaimbiwa (<i>Ficus creata</i> f. <i>sieboldii</i>)	113	-	-	132	116	123	123	-	-	479	536	508	508	-	-	378	467	426	426
	114	-	-	104	104	104	104	-	-	562	529	545	545	-	-	433	422	428	428
AVG		-	-	118	110	113	113	-	-	520	533	527	527	-	-	406	445	427	427
Nanaminoki (<i>Ilex chinensis</i>)	115	-	-	91	87	89	89	-	-	531	545	539	539	-	-	440	473	456	456
	116	-	-	87	94	91	91	-	-	578	551	562	562	-	-	469	432	449	449
AVG		-	-	89	91	90	90	-	-	555	548	551	551	-	-	455	452	452	452
Inutsuge (<i>Ilex crenata</i>)	117	-	-	63	85	74	74	-	-	593	532	562	562	-	-	482	519	500	500
	118	-	-	70	89	79	79	-	-	588	512	548	548	-	-	482	515	500	500
AVG		-	-	67	87	76	76	-	-	590	522	555	555	-	-	358	366	362	362
Tsukushinutsuge (<i>Ilex crenata</i> var. <i>fukusanana</i>)	119	-	-	66	75	71	71	-	-	655	608	629	629	-	-	357	352	354	354
	120	-	-	58	63	60	60	-	-	704	646	675	675	-	-	419	438	429	429
AVG		-	-	62	69	66	66	-	-	679	627	652	652	-	-	516	473	494	494
Soyogo (<i>Ilex pedunculosa</i>)	121	-	-	75	89	82	82	-	-	571	558	565	565	-	-	510	474	493	493
	122	-	-	53	72	62	62	-	-	673	614	645	645	-	-	513	473	493	493
AVG		-	-	64	80	72	72	-	-	622	586	605	605	-	-	541	500	522	522
Kuroganemochi (<i>Ilex rotunda</i>)	123	-	-	99	119	110	110	-	-	531	474	499	499	-	-	638	560	601	601
	124	-	-	94	105	100	100	-	-	544	512	528	528	-	-	589	530	561	561
AVG		-	-	97	112	105	105	-	-	538	493	513	513	-	-	374	392	386	386
Inuunemodoki (<i>Ilex serrata</i> f. <i>argentea</i>)	125	-	-	63	137	88	88	-	-	515	446	489	489	-	-	408	416	413	413
	126	-	-	85	98	91	91	-	-	438	545	488	488	-	-	391	404	399	399
AVG		-	-	74	117	89	89	-	-	476	496	489	489	-	-	507	670	691	691
Shikimi (<i>Ulmus anisatum</i>)	127	-	-	89	130	106	106	-	-	563	472	520	520	-	-	632	633	632	632
	128	-	-	80	109	94	94	-	-	616	532	574	574	-	-	669	651	662	662
AVG		-	-	85	119	100	100	-	-	589	502	547	547	-	-	411	436	424	424
Nezumimochi (<i>Ligustrum japonicum</i>)	129	-	-	61	63	62	62	-	-	671	646	659	659	-	-	437	434	436	436
	130	-	-	61	60	60	60	-	-	662	647	654	654	-	-	424	435	430	430
AVG		-	-	61	62	61	61	-	-	667	646	657	657	-	-	783	727	751	751
Kanagunimochi (<i>Lindera erythrocarpa</i>)	131	-	-	65	88	77	77	-	-	438	448	443	443	-	-	717	681	700	700
	132	65	66	76	111	93	81	432	468	451	508	461	483	467	-	750	704	725	725
AVG		65	66	70	99	85	85	432	468	451	473	454	463	455	-	512	522	489	425
Aburachan (<i>Lindera praecox</i>)	133	-	-	75	76	75	75	-	-	520	526	523	523	-	-	511	505	508	508
	134	-	-	56	81	69	69	-	-	488	522	506	506	-	-	500	465	481	490
AVG		-	-	66	78	72	72	-	-	504	524	514	514	-	-	520	472	493	493
Shiromoji (<i>Lindera triloba</i>)	135	-	-	72	92	81	81	-	-	525	519	522	522	-	-	428	486	459	459
	136	-	-	69	77	73	73	-	-	500	517	509	509	-	-	474	479	476	476
AVG		-	-	70	84	77	77	-	-	512	518	516	516	-	-	562	563	563	563
Baribermochi (<i>Litsea acuminata</i>)	137	-	-	71	74	73	73	-	-	397	459	427	427	-	-	386	595	479	479
	138	-	-	87	71	78	78	-	-	359	440	400	400	-	-	474	579	521	521
AVG		-	-	79	73	76	76	-	-	378	450	414	414	-	-	675	686	680	680
Kagonoki (<i>Litsea coreana</i>)	139	-	-	82	97	90	90	-	-	386	404	395	395	-	-	676	659	667	667
	140	-	-	78	99	89	89	-	-	424	443	434	434	-	-	676	672	673	673
AVG		-	-	80	98	89	89	-	-	405	424	415	415	-	-	591	591	601	601
Tabunoki (<i>Machilus thunbergii</i>)	141	-	-	62	92	78	78	-	-	491	459	474	474	-	-	591	646	620	620
	142	-	-	69	86	79	79	-	-	451	454	453	453	-	-	601	618	610	610
AVG		-	-	66	89	78	78	-	-	471	456	463	463	-	-	-	-	-	-

Conclusion

This paper presents green moisture content and basic density data for 95 woody species, including three woody lianas, collected from Kyushu University Forests, which ranges from a warm temperate forest zone to a cool temperate forest zone, during July and August from 2003 to 2006. Many data are previously unreported, which means this dataset contains scientifically important information.

References

- Forestry and Forest Products Research Institute (2004) Wood industry handbook (tentative translation by the authors from the original Japanese title). 4th revised edition. Maruzen Company, Tokyo, 192
- Fushitani M, Kikata Y, Okano T, Sado T, Takemura T, Norimoto M, Arima T, Tsutsumi J & Hirai N (1985) Textbook of wood physics (tentative translation by the authors from the original Japanese title). Buneido Publishing, Tokyo
- Gibbs RD (1958) Patterns in the seasonal water content of trees. In: The physiology of forest trees. Thimann KV (ed) The Ronald Press, New York, 43-69
- Kano T (1987) Tree breeding considering wood quality (tentative translation by the authors from the original Japanese title). Forestry Science and Technology Institution, Ibaraki, 99 pp
- Kawazumi K, Oda K & Tsutsumi J (1991) Heartwood properties of sugi (*Cryptomeria japonica*): moisture content of green wood, hot water extractives and lightness (in Japanese with English summary). Bull Kyushu Univ For 64:29 - 39
- Miyajima H (1992) Understanding wood: For forester and wood users (tentative translation by the authors from the original Japanese title). Hoppou Ringyo Kai, Sapporo, 176 p.
- Nakada R (2006) Within-stem water distribution in living trees of some conifers. IAWA J. 27(3): 313 - 327
- Nakada R, Fujisawa Y & Hirakawa Y (1999) Soft X-ray observation of water distribution in the stem of *Cryptomeria japonica* D. Don I: General description of water distribution. J Wood Sci 45: 188 - 193
- Nakai T & Yamai Ryozauro (1982) Properties of the important Japanese woods. The mechanical properties of 35 Japanese important woods (in Japanese). Bull For & For Prod Res Inst 319:13 - 46
- Tyree MT & Zimmermann MH (2002) Xylem structure and the ascent of sap. Springer-Verlag, Berlin. 283 p.
- Umebayashi, T., Utsumi, Y., Koga, S., Inoue, S., Fujikawa, S, Arakawa, K., Matsumura, J., & Oda, K. (2008) Xylem water conducting pathways of deciduous broadleaved trees growing in a northern temperate zone. IAWA J 29 (3): 247 - 263
- Umebayashi, T., Utsumi, Y., Koga, S., Inoue, S., Matsumura, J., Oda, K., Fujikawa, S, Arakawa, K. & Otsuki, K. (2010) Xylem water-conducting pattern of 34 broadleaved evergreen species in southern Japan. Trees 24: 571 - 583
- Watanabe H (1978) General wood science (tentative translation by the authors from the original Japanese title), Nourin shuppan, Tokyo, 627 p.
- Yazawa K (1960) The seasonal water content of sapwood and heartwood of broad-leaved trees, especially of beech (*Fagus crenata Blume*) (in Japanese with English abstract). Mokuzai Gakkashi 6(4): 170 - 175
- Yazawa K, Ishida S, Miyajima H (1965) On the wet-wood of some broad-leaved trees grown in Japan I. Mokuzai Gakkaishi 11(3):71 - 76
- Yazawa K, Ishida S (1965) On the wet-heartwood of some broad-leaved trees grown in Japan II. J Fac Agr Hokkaido Univ 54(2):123 - 136
- Zhang SY (1997) Wood quality: Its definition, impact, and implications for value-added timber management and end uses. Part I: Its definition and impact. Proceedings of the CTIA/IUFRO International Wood Quality Workshop (ed) Zhang SY *et al*. Forintek Canada, Qubec city, I: 17 - 39
- Zobel, BJ., van Buijtenen, JP (1989) Wood Variation. Its Causes and Control. Springer-Verlag, Berlin, Heidelberg, 363 pp
- Zobel, BJ., van Sprague, JR (1999) Juvenile wood in forest trees. Springer-Verlag, Berlin, 300 pp